



## SPECIFICATION

GRADE	CKT-80	TEST METHOD
Brightness (% ISO )	92 ±2	DIN 53 163-1977
Color	White	
Yellow Index	2.2 to 2.5	
pH- value	6 - 7	ISO 787/Lx-1981
Bulk Density (gms/Ltr)	300 to 340	DIN 468
Specific Gravity	2.6	ISO 787/X-1981
Moisture (% Max.)	0.5	ISO 787/11-1981
Wet sieve residues 325 Mesh	0.5 - 1	
Oil Absorption (gm / 100 gm)	55 – 65	ISO 787/V-1980
Average particle size d50	1.6	Sedigraph-5100
2 Microns (% min.)	48 – 52	

[sales@mineraltechniques.com](mailto:sales@mineraltechniques.com)

[info@mineraltechniques.com](mailto:info@mineraltechniques.com)