



SPECIFICATION

GRADE	LKT-70	TEST METHOD
Brightness (% ISO)	90 ±1	DIN 53 163-1977
Color	White	
pH- value	6 – 7	ISO 787/Lx-1981
Bulk Density (gms/Ltr)	290 – 330	DIN 468
Moisture (% Max.)	0.5	ISO 787/11-1981
Wet sieve residues 325 Mesh	0.05 – 0.01	
Conductivity (µs/cm)	100 Max	
Average particle size d50	1.5	Sedigraph-5100
2 Microns (% min.)	58	
Specific surface area, BET (m ² / gm)	11 ±2	BET

sales@mineraltechniques.com

info@mineraltechniques.com